

	No.	PROVENANCE		cu	Sn	Sb	Pb	Co	Ni	Fe	Ag	Au	Zn	Bi	As	Incs.	State
DAMARC	1	ABSM/CA31-32/L 120 cms	Hair piece	87.18	10.12	0.00	0.05	ti	0.08	0.00	0.02	0.00	0.02 +	0.02	0.08	-----	
DAMARC	2	ABSM/CA31-32/L 120 cms	Bronze needle	89.47	8.81	0.09	1.31	0.00	0.05	ti	0.05	ti	0.02 +	0.02 +	0.18	-----	
DAMARC	3	ABSM/CA31-32/L 120 cms	Bronze needle	89.75	9.85	0.00	0.08	0.01	0.03	0.02	0.07	ti	ti	0.01	0.18	-----	
DAMARC	4	ABSM/CA24/L Talayotic	Bronze needle	90.22	9.52	0.00	0.06	ti	0.02	0.03	0.07	0.00	0.03 +	0.03	0.15	-----	
DAMARC	5*	ABSM/CA24/L Talayotic	Bronze Chest	71.60	27.60	0.00	0.17	0.03	0.10	0.07	0.00	0.00	0.07	0.02	0.34	-----	*Corrosion product only.
DAMARC	6	ABSM/CA42/L	Handle of awl	99.63	0.00	0.01	0.03	0.01	0.04	0.00	0.09	0.04	ti	0.03	0.12	-----	
DAMARC	7	ABSM/CA42/L	Point of awl	91.71	7.68	0.40	ti	ti	0.08	ti	0.06	0.00	0.00	ti	0.07	-----	
DAMARC	8*	ABSM/CA26-27/L Rubble Fill of Talayotic Wall	Bronze frac	99.58	0.00	0.00	0.06	0.00	0.02	0.00	0.08	0.00	0.00	0.00	0.26	-----	*Corrosion product only.
DAMARC	9	ABSM/CA34/L 40 cms	Bronze horn	93.89	5.66	0.00	0.09	0.01	0.07	0.01	0.05	0.15	0.03 +	0.00	0.04	-----	
DAMARC	10	ABSM/CA37/L 40 cms	Hair piece	88.37	10.64	0.05	0.66	ti	0.05	ti	0.05	0.00	0.00	ti	0.18	-----	
DAMARC	11*	ABSM/CA35/L 40 cms Post Talayotic	Bronze bead	99.59	0.00	0.00	0.26	0.00	0.00	0.02	0.02	0.04	0.00	0.00	0.07	-----	*Corrosion product only.
DAMARC	12	ABSM/CA /L Post Talayotic	Bronze nail	88.55	10.10	0.04	1.11	0.00	0.04	0.00	0.03	0.00	ti	ti	0.13	-----	
DAMARC	13	ABSM/CA37/P Rock Post Talayotic	Tratinabulum	92.27	7.14	0.03	0.30	ti	0.08	0.01	0.06	ti	0.00	0.01 +	0.10	-----	
DAMARC	14	ABSM/CA26-27/L 100 cms	Bronze piece	88.50	11.27	0.00	0.00	0.01	ti	0.01	0.04	0.00	ti	0.04	0.13	-----	
DAMARC	15	ABSM/CA26-27/L 100 cms	Tratinabulum	91.43	7.70	0.04	0.60	0.01	0.07	0.02	0.06	0.00	0.04	0.02 +	0.10	-----	
DAMARC	16	ABSM/CA11-16/L	Tratinabulum	94.22	5.31	0.04	0.05	0.02	0.08	ti	0.13	0.02 +	0.00	0.01 +	0.12	-----	
DAMARC	17	ABSM/CA 30/L	Bronze nail	95.31	4.21	0.01	0.13	0.01	0.10	0.08	0.05	0.02 +	0.00	0.01 +	0.07	-----	
DAMARC	18	ABSM/CA 30/L	Bronze frac	90.04	8.95	0.03	0.50	0.01	0.08	0.08 +	0.03	ti	0.06 +	0.00	0.22	-----	
DAMARC	19	ABSM/CA 30/L	Tratinabulum	90.46	8.91	0.05	0.20	0.01 +	0.08	0.02	0.06	0.02 +	0.03 +	0.01 +	0.15	-----	
DAMARC	20*	ABSM/CA 23/L 80-90 cms	Frag	52.75	46.69	0.00	0.00	0.00	0.03	0.03	0.04	0.00	0.06	0.00	0.40	-----	*Corrosion product only.
DAMARC	21	ABSM/CA 22/L	Bronze spiral	90.15	8.69	0.09	0.75	0.01	0.06	0.00	ti	0.07 +	0.00	0.01 +	0.17	-----	
DAMARC	22*	ABSM/CA 23/L 80-90 cms	Piece of coil	99.54	0.04	0.00	0.09	0.00	0.04	0.01	0.02	0.24	0.02	0.00	0.00	-----	*Corrosion product only.
DAMARC	23	ABSM/CA 45-6/L 50 cms	Needle	90.03	9.06	0.04	0.12	0.00	0.07	0.27	0.09	0.11 +	ti	0.01 +	0.20	-----	
DAMARC	24	ABSM/CA 24/L Fisure zone at 'j' rock	Needle	95.83	3.78	0.00	0.14	0.01	0.06	0.05	0.07	0.00	0.00	0.04	0.02	-----	
DAMARC	25	ABSM/CA 24-27/L Fisure zone at 'j' rock	Needle	93.67	4.98	0.08	0.77	0.01	0.02	0.00	0.07 +	0.14 +	ti	0.01 +	0.30	-----	
DAMARC	26	ABSM/CA 24/ Tall wall / Talayotic	Frag	98.81	0.00	0.03	0.32	ti	0.02	0.32	0.04	0.00	0.03	0.00	0.43	-----	
DAMARC	27*	ABSM/CA 33/L 40 cms	Tratinabulum	99.83	0.07	0.00	0.05	0.00	0.00	0.00	0.00	0.00	0.03	0.00	0.02	-----	*Corrosion product only.
DAMARC	28	SON PUIG /PRT / Inferior Level	Laurel leaf Dagger	97.00	2.66	0.01	ti	ti	0.02	0.01	0.11	ti	0.00	0.06	0.13	-----	
DAMARC	29	LLUCHMAJOR	Tratinabulum	99.37	0.03	0.05	0.09	0.01	0.01	0.09	0.04	0.05 +	0.03	0.00	0.23	-----	
DAMARC	30	ABSM /CA 33/L 40 CMS	Tratinabulum	92.08	0.78	0.18	6.50	ti	0.05	0.00	0.10	0.04	0.02 +	0.00	0.25	-----	
DAMARC	31	ABSM / / L	Tratinabulum	94.69	4.96	ti	0.19	ti	0.08	ti	0.00	0.00	0.00	0.00	0.08	-----	
DAMARC	32*	ABSM / / L	Sword	0.00	Solo Cu	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	-----	*Corrosion product only.
DAMARC	33	ABSM /CA 21/L	Staple ?	93.94	5.55	0.07	0.03	ti	0.08	0.20	0.07	ti	ti	0.01	0.05	-----	
DAMARC	34	ABSM / / L	Strap	89.01	6.65	0.05	3.31	0.02	0.05	0.42	0.11	0.08	0.00	0.00	0.30	-----	
DAMARC	35	ABSM / / L	Bull's horn	92.16	6.97	0.08	0.26	0.01	0.08	0.01	0.11	0.13	0.02 +	0.02	0.15	-----	
DAMARC	36	ABSM / / L 40 CMS	Chain track	96.71	2.97	0.07	0.02	0.01	0.06	ti	0.04 +	ti	0.00	0.01 +	0.11	-----	
DAMARC	37	ABSM / / L	Tratinabulum	87.62	7.43	0.06	4.41	ti	0.06	0.04	0.04	0.21 +	0.00	0.03 +	0.30	-----	
DAMARC	38	ABSM / / L	Knife blade	85.79	13.45	0.11	0.19	ti	0.06	ti	0.18	0.05 +	0.02 +	0.02 +	0.13	-----	
DAMARC	39*	ABSM /CA 21/L	Brooch	98.96	0.31	0.00	0.35	0.00	0.00	0.00	0.14	0.09	0.00	0.01	0.14	-----	*Corrosion product only.
DAMARC	40*	ABSM / / L	Spear head	93.29	5.84	0.07	0.55	0.01	0.00	0.01	0.00	0.00	0.02	0.00	0.21	-----	*Corrosion product only.
DAMARC	41	ABSM /CA 22/L	Spiral	90.06	8.64	0.05	0.77	0.00	0.08	0.00	0.05	0.08	0.02	0.01 +	0.24	-----	
DAMARC	42	ABSM /CA 26-7/L	Spiral	91.72	7.16	0.08	0.52	0.01	0.06	ti	0.02 +	0.00	0.02	0.06	0.35	-----	
DAMARC	43	ABSM /CA /L	Disc Tratinabulum	82.89	11.04	0.03	5.40	0.01	0.08	ti	0.07	0.04 +	0.00	0.05 +	0.39	-----	
DAMARC	44	ABSM /CA /L	Pin	86.64	12.24	0.64	0.03	0.01	0.08	0.00	0.09	ti	0.00	0.00	0.27	-----	
DAMARC	45	SFO/ OS.81/Gred 2 G3	Metal frac	91.66	6.45	ti	0.30	ti	0.04	0.00	0.09	0.05 +	ti	0.03	1.38	Zn rach?	